



Atlant

Fremstillingsmåde	Tuftet 1/10" saxony	Manufacturing process	Tufted 1/10" saxony
Luvmateriale	100% PA	Pile material	100% PA
Bagside	PF	Backing	PF
Luvvægt / m²	ca. 1000 gr	Pile weight / m²	app. 1000 gr
Luvhøjde (ISO 1766-1999)	ca. 6 mm	Pile height	6 mm
Totalvægt / m² (ISO 8543-1998, clause 6)	ca 2160 gr	Total weight / m²	app. 2160 gr
Totaltykkelse (ISO 1765)	ca. 8,5 mm	Total Height	app 8,5 mm
Løkkeantal / m² (ISO 1763-1986)	ca. 200.940	Number of tufts / m²	app 200.940
Bredde	ca. 400 cm	Width	app 400 cm
Brandklasse (EN 13501-1)	B _{fl} -s1	Flammability test	B _{fl} -s1
Antistatiske egenskaber (ISO 6356)	< 2 kV	Stroll test	< 2 kV
Lysægtthed	> 5-6	Lightfastness	> 5-6
Gnidægthed, våd	>4-5	Rubbing fastness wet	> 4-5
Vådægthed, farveændring	> 4	Waterfastness change in colour	> 4
Gnidægthed, tør	≥ 4-5	Rubbing fastness dry	> 4-5
Trinlydsdæmpning	+/- 28 dB	Impact sound insulation	+/- 28 dB
Lydabsorption (alfa-s 1000 hz)	+/- 0,30	Sound absorption (alfa-s 1000 hz)	+/- 0,30
Lydabsorption (alfa-w 1000 hz)	+/- 0,25	Sound absorption (alfa-w 1000 hz)	+/- 0,25
Varmeledningsmodstand	+/- 0,112 m ² /kW	Thermal retention	+/- 0,112 m ² /kW
TOG	+/- 1,12	TOG rating	+/- 1,12
Permanent antistatisk	>2 kV	Permanently antistatic	>2 kV
Modstand til jord (ISO/DIS 10965)	<10 ⁹ Ohm	Surface resistance RoT	<10 ⁹ Ohm



DOP-CPR-1038-111910
EN 14041

