



## Aurora

<b>Fremstillingsmåde</b>	Tuftet 1/10" cut pile	<b>Manufacturing process</b>	Tufted 1/10" cut pile
<b>Luvmateriale</b>	100% PA	<b>Pile material</b>	100% PA
<b>Bagside</b>	PF	<b>Backing</b>	PF
<b>Luvvægt / m<sup>2</sup></b>	ca. 450 gr	<b>Pile weight / m<sup>2</sup></b>	app. 450 gr
<b>Luvhøjde (ISO 1766-1999)</b>	ca. 4 mm	<b>Pile height</b>	4 mm
<b>Totalvægt / m<sup>2</sup> (ISO 8543-1998, clause 6)</b>	ca 1650 gr	<b>Total weight / m<sup>2</sup></b>	app. 1650 gr
<b>Totaltykkelse (ISO 1765)</b>	ca. 7 mm	<b>Total Height</b>	app 7 mm
<b>Løkkeantal / m<sup>2</sup> (ISO 1763-1986)</b>	ca. 204.880	<b>Number of tufts / m<sup>2</sup></b>	app 204.880
<b>Bredde</b>	ca. 400 cm	<b>Width</b>	app 400 cm
<b>Brandklasse (EN 13501-1)</b>	Cfl-s1	<b>Flammability test</b>	Cfl-s1
<b>Antistatiske egenskaber (ISO 6356)</b>	< 2 kV	<b>Stroll test</b>	< 2 kV
<b>Lysægthed</b>	> 5-6	<b>Lightfastness</b>	> 5-6
<b>Gnidægthed, våd</b>	>4-5	<b>Rubbing fastness wet</b>	> 4-5
<b>Vådægthed, farveændring</b>	≥ 4	<b>Waterfastness change in colour</b>	> 4
<b>Gnidægthed, tør</b>	> 4-5	<b>Rubbing fastness dry</b>	> 4-5
<b>Trinlydsdæmpning</b>	+/- 28 dB	<b>Impact sound insulation</b>	+/- 28 dB
<b>Lydabsorption (alfa-s 1000 hz)</b>	+/- 0,53	<b>Sound absorption (alfa-s 1000 hz)</b>	+/- 0,53
<b>Lydabsorption (alfa-w 1000 hz)</b>	+/- 0,25	<b>Sound absorption (alfa-w 1000 hz)</b>	+/- 0,25
<b>Varmeledningsmodstand</b>	+/- 0,07 m <sup>2</sup> /kW	<b>Thermal retention</b>	+/- 0,07 m <sup>2</sup> /kW
<b>TOG</b>	+/- 0,7	<b>TOG rating</b>	+/- 0,7

